

CS STANDARD PRODUCTS

TECHNICAL CORKS



CS MICRO 0.5-2.0 mm

The CS Micro 0.5-2.0mm closure offers exemplary sealing capacities, top mechanical function and consistent sensory performance.

Its body is crafted by molding micro-granules of 0.5 to 2.0mm into an agglomerated cork.

	TEST	METHOD	SPECIFICATION	AQL
SENSORY PROPERTIES	RELEASABLE TCA ⁽¹⁾	ISO 20752	≤ 1.0 ng/L	N.A.
DIMENSIONAL PROPERTIES	LENGTH (STANDARD)	ISO 9727-1; ISO 2859; ISO 16420	38 / 44 +/- 0.5 mm	4.0
	DIAMETER (STANDARD)	ISO 9727-1; ISO 2859; ISO 16420	24 +/- 0.3 mm	1.5
PHYSICAL PROPERTIES	GRANULE SIZE	Internal	0.5 - 2.0 mm	N.A.
	DENSITY	ISO 9727-2; ISO 2859; ISO 16420	245 - 305 kg/m ³	4.0
	MOISTURE CONTENT	ISO 9727-3; ISO 2859; ISO 16420	< 7.0 %	2.5
	TORSION	NP 2803-6; ISO 2859	≥ 22 daN.cm	N.A.
	EXTRACTION FORCE ⁽²⁾	ISO 9727-5; ISO 2859	15 - 35 daN	N.A.
	OXIDANTS	Internal	N.D.	N.A.

AVAILABLE WASHES



Alpha

100% of our granules undergo the *Vapex* process.

⁽¹⁾ Average value - ISO 20752 | ⁽²⁾ Lots > 10,000 corks

N.D. - Not detectable | N.A. - Not applicable | AQL - Acceptable Quality Level

Edition: March 2019